

Xyron™ 540V

聚苯醚 + PS

Asahi Kasei Chemicals Corporation

Technical Data

总体

材料状态	• 已商用 : 当前有效
资料 ¹	• Technical Datasheet (English) • Processing - Xyron (English)
UL Yellow Card ²	• E82268-250792
Search for UL Yellow Card	• Asahi Kasei Chemicals Corporation • Xyron™
供货地区	• 北美洲 • 非洲和中东 • 欧洲 • 亚太地区
添加剂	• 阻燃
性能特点	• 阻燃性能
加工方法	• 注射成型

物理性能	额定值 (英制)	额定值 (公制)	测试方法
密度	1.08 g/cm ³	1.08 g/cm ³	ISO 1183
收缩率 ⁴ (0.0787 in (2.00 mm))	0.50 到 0.70 %	0.50 到 0.70 %	Internal Method
吸水率 (73°F (23°C), 24 hr)	0.10 %	0.10 %	ISO 62
室外适用性 (Black)	f2	f2	UL 746C

机械性能	额定值 (英制)	额定值 (公制)	测试方法
拉伸应力 (屈服, 73°F (23°C))	8700 psi	60.0 MPa	ISO 527-2
断张率 (73°F (23°C))	13 %	13 %	ISO 527-2
弯曲模量 (73°F (23°C))	352000 psi	2430 MPa	ISO 178
弯曲强度 (73°F (23°C))	14200 psi	98.0 MPa	ISO 178

冲击性能	额定值 (英制)	额定值 (公制)	测试方法
简支梁缺口冲击强度 ⁵ (73°F (23°C))	7.1 ft-lb/in ²	15 kJ/m ²	ISO 179

热性能	额定值 (英制)	额定值 (公制)	测试方法
热变形温度			
264 psi (1.8 MPa), 未退火	248 °F	120 °C	ASTM D648
264 psi (1.8 MPa), 未退火	237 °F	114 °C	ISO 75-2/A
线形膨胀系数 - 流动 (-22 到 149°F (-30 到 65°C))	0.000039 in/in/°F	0.000070 cm/cm/°C	ISO 11359-2

电气性能	额定值 (英制)	额定值 (公制)	测试方法
表面电阻率	1.0E+16 ohm	1.0E+16 ohm	IEC 60093
体积电阻率 (73°F (23°C))	1.0E+16 ohm·cm	1.0E+16 ohm·cm	IEC 60093
耐电强度 ⁶ (0.0787 in (2.00 mm))	740 V/mil	29 kV/mm	IEC 60243-1
介电常数			IEC 60250
100 Hz	2.90	2.90	
1 MHz	2.90	2.90	
耗散因数			IEC 60250
100 Hz	0.0030	0.0030	
1 MHz	0.0040	0.0040	


可燃性	额定值 (英制)	额定值 (公制)	测试方法
UL 阻燃等级 (0.0287 in (0.730 mm))	V-1	V-1	UL 94

注射	额定值 (英制)	额定值 (公制)
干燥温度	194 到 212 °F	90.0 到 100 °C
干燥时间	2.0 到 4.0 hr	2.0 到 4.0 hr
加工 (熔体) 温度	464 到 572 °F	240 到 300 °C
模具温度	122 到 176 °F	50.0 到 80.0 °C

Xyron™ 540V

聚苯醚 + PS

Asahi Kasei Chemicals Corporation

 **仁捷塑胶**
电话: 18681139818

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL IDES continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.

³ 一般属性：这些不能被视为规格。

⁴ 150x150x2 mm

⁵ 4 mm

⁶ Short Time