

NORYL* FN215Z Resin

聚苯醚 + PS

SABIC Innovative Plastics Asia Pacific

Technical Data

产品说明

PPE + PS, FR foam molding grade

总体

材料状态	• 已商用 : 当前有效
资料 ¹	• Technical Datasheet
UL Yellow Card ²	• E45587-237018
Search for UL Yellow Card	• SABIC Innovative Plastics Asia Pacific • NORYL*
供货地区	• 亚太地区
性能特点	• 阻燃性能

物理性能	额定值 (英制)	额定值 (公制)	测试方法
比重	1.00	0.998 g/cm ³	ASTM D792
熔流率 (250°C/10.0 kg)	44 g/10 min	44 g/10 min	ASTM D1238
收缩率 - 流动 (0.126 in (3.20 mm))	0.0060 到 0.0080 in/in	0.60 到 0.80 %	Internal Method
吸水率 (24 hr)	0.060 %	0.060 %	ASTM D570
机械性能	额定值 (英制)	额定值 (公制)	测试方法
抗张强度 (屈服)	4700 psi	32.4 MPa	Internal Method
伸长率 (断裂)	16 %	16 %	Internal Method
弯曲模量	312000 psi	2150 MPa	ASTM D790
弯曲强度	7960 psi	54.9 MPa	ASTM D790
热性能	额定值 (英制)	额定值 (公制)	测试方法
热变形温度			ASTM D648
264 psi (1.8 MPa), 未退火, 0.252 in (6.40 mm)	203 °F	95.0 °C	
线形膨胀系数 - 流动 (-22 到 86°F (-30 到 30°C))	0.000038 in/in/°F	0.000068 cm/cm/°C	ASTM E831
电气性能	额定值 (英制)	额定值 (公制)	测试方法
表面电阻率	1.0E+17 ohm	1.0E+17 ohm	ASTM D257
介电常数 (100 Hz)	2.27	2.27	ASTM D150
可燃性	额定值 (英制)	额定值 (公制)	测试方法
UL 阻燃等级 (0.197 in (5.00 mm))	• V-1 • 5VA	• V-1 • 5VA	UL 94

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL IDES continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.

³ 一般属性：这些不能被视为规格。